

STEP-GROWTH POLYMERIZATION

Reliable Parts. Reliable People.

TECHNICAL ARTICLES | PROPERTIES OF PLASTICS

Step-growth polymerization forms polymers in a manner that is quite different from chain-growth polymerization. The mechanism requires that at least two different monomers participate in the reaction¹. Before we consider the specific steps in step-growth polymerization, we'll first consider the necessary functional groups required in the monomers for the reaction(s) to occur.

Each stage in step-growth polymerization involves a reaction between dissimilar chemical groups which are part of the monomer molecules². The chemical groups are termed "functional groups" due to the fact they provide a specific attribute (functionality) that allows them to react together in a specific way to give the desired resin properties.

The most common type of reaction in forming resin via step-growth polymerization involves the formation of a new bond (covalent bond) between the two functional groups. Simultaneously, a by-product is produced from the reaction (sometimes water – which is why this polymerization is sometimes termed condensation polymerization). Let's illustrate this by looking at a generic alcohol and acid:

(alcohol) (acid) (ester) (water
$$-C-O-H + H-O-C \longrightarrow -C-O-C + H_2O \bigcirc$$
 New bond

Two other types of monomers that combine via step-growth polymerization are an amine and an acid to form an amide:

Water is not the only by-product that might be produced, however. Here's an example of a step-growth polymerization where an alcohol by-product is produced:

(terephthalate) (alcohol) (PETI) (alcohol)
$$\begin{matrix} H \\ I \\ -C-O-C-H \\ I \\ H \end{matrix} + H-O-C- \longrightarrow -C-C-O-H \\ + H-O-C-H$$

A particular step-growth polymerization reaction of great historical and commercial significance is the polymerization of nylon. This reaction uses two symmetric bifunctional monomers (hexamethylene diamine and adipic acid). The resulting material is a polyamide, commonly known as nylon 6,6; the numerical designation in the name represents the number of carbons in each monomer.

Typical resins polymerized via step-growth include: acetals, nylons, polycarbonate, and polyesters.

Our next discussions will involve specific resins and how they perform both physically and mechanically. The resins to be presented have all been formed via the step-growth or chain-growth polymerization method; which in turn will have an effect on its strengths and weaknesses.

www.steinwall.com

- F (763) 767-7061
- **P** (763) 767-7060 | (800) 226-9199
- E sales@steinwall.com
- A 1759 116th Ave. NW Coon Rapids, MN 55448

¹ Askeland, Donald R., The Science and Engineering of Materials, PWS Publishing Company, 1994.

² Strong, A. Brent, Plastics: Materials and Processing, Prentice Hall, 2000.